



RUST-OLEUM® CHALKED MATT PAINT

DESCRIPTION AND USES

Rust-Oleum® Chalked Ultra Matt Paint creates an ultra matt finish with excellent coverage and adhesion. It transforms and rejuvenates furniture and home décor with a smooth matt finish. Chalked Ultra Matt Paint provides one coat coverage on most surfaces without special surface preparation or priming. It can be painted or distressed, giving any project a one-of-a-kind look. Use on wood, metal, ceramic, glass, canvas and more. **For interior use only.**

PRODUCTS

SKU	DESCRIPTION
305257	Linen White
305259	Serenity Blue
305271	Blush Pink
305273	Charcoal
305274	Aged Grey
347691	Coastal Blue
347693	Chiffon Cream
383231	Tate Green
383232	Harbour Blue
393419	Black Abyss
393420	Rainforest Green
393421	Oat Latte

PRODUCT APPLICATION

READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT

SURFACE PREPARATION

Remove all dirt, grease, oil, salt, and chemical contaminants by washing the surface with soap and water and let dry. Remove loose paint and rust with a wire brush or sandpaper. To enhance adhesion, lightly sand glossy or porous surfaces. Special precautions should be taken during surface preparation of pre-1960 painted surfaces as they may contain harmful lead. Avoid the inhalation of dust. Wear a suitable face mask if dry sanding. Remove any wax by lightly wiping the surface with mineral turps.

PRODUCT APPLICATION (cont.)

PRIMING

Priming is not required for most surfaces. For excellent coverage, use of a Rust-Oleum primer can be used on surfaces such as treated wood, bare metal, and treated wood. When applying a light colour over a dark surface, a primer is required to prevent tannin bleed. The coating can be applied 2 hours after applying the primer.

APPLICATION

Use in a well-ventilated area when temperature is between 10°C and 32°C and humidity is below 85% to ensure proper drying. Stir thoroughly to ensure any settled pigment is redispersed. Do not shake the can. Thinning is not required. In hot, dry conditions, you may thin with up to 60 mL fresh water per litre to extend the dry time. Avoid painting in direct sunlight or on hot surfaces.

Use a high-quality synthetic brush. Roller application is not recommended. Avoid excessive brushing as this will reduce film thickness and protection. Use light even brush strokes to ensure even flow and the smoothest finish. Only one coat is required, but up to 3 coats can be applied for the desired look. Wait 30 minutes between each coat.

DRY & RECOAT

Dry and recoat times are based on 25°C and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 30 minutes, to handle in 1 hour and is fully dry in 2-4 hours. May be recoated after 2-4 hours. The finish coat is fully dry in 2-4 hours. Chalked Protective Topcoat can be applied for added protection. Apply according to instructions on the can.

DISTRESSING

This paint can be distressed if desired. To distress the surface, lightly sand the surface with fine to medium grit sandpaper or a sanding sponge. The more the piece is distressed, the more the original surface will show through. Wait 2 hours before sanding or distressing. Top coat with Chalked Protective Topcoat for added durability.

CLEAN-UP

Clean brush and other and application tools immediately with soap and water.

COVERAGE

Up to 14 square metres.

	TECHNICAL DATA	CHD-04
	RUST-OLEUM® CHALKED MATT PAINT	

PHYSICAL PROPERTIES

		CHALKED ULTRA MATT PAINT
Resin Type		Acrylic
Pigment Type		Titanium Dioxide and Inerts
Solvents		Water, Glycol Ethers
Weight	Per Gallon	13.1-13.8 lbs.
	Per Liter	1.60-1.65 kg
Solids	By Weight	61.0-64.0%
	By Volume	39.0-40.0%
Volatile Organic Compounds		<750 g/l
Recommended Dry Film Thickness (DFT) per Coat		25-50µ (1.0-2.0 mils)
Wet Film to Achieve DFT (Unthinned material)		75-125 µ (3.0-5.0 mils)
Practical Coverage at Recommended DFT (assume 15% material loss)		14 square metres
Dry Times at 21-27°C and 50% Relative Humidity	Touch	30 minutes
	Handle	1 hour
	Recoat	2-4 hour
	Full Cure	2-4 hours
Shelf Life		3 years
Flash Point		93°C
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



RUST-OLEUM AUSTRALIA & NEW ZEALAND
PTY LTD
Level 2, 307 Ferntree Gully Road
Mount Waverley, Victoria 3149 Australia
PH: 1 300 784 476
Email: technical@rustoleum.com.au
www.rustoleum.com.au

Rust-Oleum New Zealand
QB Studios - Office 7
2 Morgan St
Newmarket, Auckland 1023 New Zealand
PH: 0800 787 865
Email: technical@rustoleum.co.nz
www.rustoleum.co.nz

Rust-Oleum South Africa PTY. LTD
PO Box 400 Randvaal 1873
Gauteng, South Africa
PH: 016 365 5120
Email: info@rustoleum.co.za
www.rustoleum.co.za

Form: GDH-993
Rev.: 052224